

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. (Currently Amended) A medical apparatus comprising at least one surface which is at least partially coated with a hydrolytically condensed organosilane sol-gel composition, wherein the organosilane sol-gel composition comprises a mixture of tetraethoxysilane, ~~methyltrimethoxysilane~~ methyltrimethoxysilane, and organosilane compounds that contain an organic, polymerizable substituent, wherein the organosilane compounds that contain the organic, polymerizable substituent consist of 3-glycidoxypropyl trimethoxysilane, methacryloxypropyl trimethoxysilane and vinyl trimethoxysilane, and wherein the organosilane sol-gel composition is further formed from dimethylmalonic acid.
2. (Canceled)
3. (Currently Amended) The medical apparatus according to claim 1, wherein the sol-gel composition further comprises a material is formed from a mixture of an organosilane compound and silica particles.
4. (Canceled)
5. (Previously Presented) The medical apparatus according to claim 1, wherein the coating can be cured at a curing temperature of about 80°C or lower.
6. (Canceled)

7. (Previously Presented) The medical apparatus of claim 1, wherein said surface is a tabletop of a diagnostic system.

8. (Canceled)

9. (Canceled)

10. (Canceled)

11. (Canceled)

12. (Canceled)

13. (Currently Amended) A process for making medical equipment resistant to iodine comprising coating one or more surfaces with a hydrolytically condensed organosilane sol-gel composition, wherein the organosilane sol-gel composition comprises a mixture of tetraethoxysilane, methyltrimethoxysilane, methyltrimethoxysilane, and organosilane compounds that contain an organic, polymerizable substituent, wherein the organosilane compounds that contain the organic, polymerizable substituent consist of 3-glycidoxypropyl trimethoxysilane, methacryloxypropyl trimethoxysilane and vinyl trimethoxysilane, and wherein the organosilane sol-gel composition is further formed from dimethylmalonic acid.

14. (Currently Amended) The process of claim 13 wherein said sol-gel ~~material~~ composition is a glossy material, and further comprises comprising:

~~demi-water,~~
~~itaconic acid,~~
~~ethyl alcohol,~~

~~tetraethoxysilane,~~
~~glycidoxypropyl trimethoxysilane,~~
~~silica particles, dispersion, and~~
~~wetting agent.~~

15. (Currently Amended) The process of claim 13 wherein said sol-gel material ~~composition~~ is a matte material, and further comprises ~~comprising~~:

~~demi-water,~~
~~itaconic acid,~~
~~ethyl alcohol,~~
~~tetraethoxysilane,~~
~~glycidoxypropyl trimethoxysilane,~~
~~silica dispersion particles and a~~
~~matting agent, and~~
~~wetting agent.~~